



OWATROL® E-B

MIX-IN BONDING PRIMER

Product description

OWATROL® E-B is a high penetrating, stir-in paint additive for use in water-based masonry or interior paints, to help alleviate peeling problems on sound but chalky, powdery or porous surfaces. OWATROL® E-B provides a bonding primer, stirs in easily, and does not alter the original colour. It offers a time-saving benefit by eliminating the need to separately prime.

Properties

- Provides a bonding primer and a first flat coat of masonry or interior paint in one.
- Stabilises chalky, powdery or porous surfaces and reduces peeling problems.
- Maximises adhesion between the first and second coats.
- Recoatable after 4 hours.
- Improves durability of the finish.

Basic uses

- For exterior or interior use.
- Apply OWATROL® E-B modified paint over sound but chalky paint (emulsion or oil); distemper; sandblasted masonry or weathered, but sound asbestos cladding.
- Ideal for repainting chalky aluminum cladding, plywood or hardboard cladding and cementitious cladding.

Technical data

Finish: N/A
Vehicle type: Water/oil mixture
Solvent type: Water
Specific gravity: 0.953 ±0.01
Physical state: Semi-liquid
Flammability: Not classed as flammable
Flash point: > 63°C
Shelf life: 1-year minimum in original unopened packaging
Container size: 1L, 2L5, 10L
Colour: Creamy white
Odour: Mild solvent odour
VOC: UE limit value for this product (cat. A/h) 750 g/L. (2010). This product contains max. 220 g/L.

Good application practice

- Follow directions on the paint label.
- Wash protected areas (overhangs, porch ceilings, etc.) with detergent and water. Rinse thoroughly before painting.
- To treat mildew make a solution of 1 part bleach to 3 parts fresh water to this add detergent. Allow this solution to remain on the surface for 10-15 minutes. Rinse thoroughly with fresh water and allow washed areas to dry before painting.
- Avoid contact with eyes and skin, and provide adequate ventilation.

Application

NOTE: Use only in the first coat of paint

- Shake container well.
- Always mix a small amount of OWATROL® E-B with paint to test compatibility.
- Mix 1 part OWATROL® E-B to 4 parts paint.
- Stir paint and OWATROL® E-B mixture thoroughly. If paint thickens add enough water to return paint to its original consistency.
- Apply paint as usual.
- Apply any additional coats without OWATROL® E-B. Apply additional coats when the OWATROL® E-B/paint mixture is dry.
Do not apply more paint while the OWATROL® E-B/paint mix film feels soft or tacky.

Coverage

Coverage will vary with the texture and porosity of the surface. Generally 20% less material is used than if the paint or stain had been applied without OWATROL® E-B.

Restrictions

- Only use OWATROL® E-B in the first coat.
- Do not add OWATROL® E-B to water-based gloss paints for one coat work.

Storage

- Store unused portion in tightly closed container.
- Keep from freezing.

Safety

Keep out of reach of children.

Do not breathe vapours. Avoid contact with skin.

If swallowed, do not induce vomiting: Seek medical advice immediately and show this container or label.

MSDS available at www.owatrol.com



OWATROL INTERNATIONAL SLU

08011 Barcelone - Espagne

T. +34 93 445 17 85 - F. +34 93 445 17 80

OWATROL® E-B is a trademark:



Find all our solutions:

www.owatrol.com