



DEKS OLJE® D.1

SATURATING WOOD OIL



PRODUCT DESCRIPTION

DEKS OLJE® D.1 is an oil, which saturates the wood, literally feeding it with oil to replace those lost. Driving out moisture and air, filling the woods pores with oil, it enriches and stabilises to provide long lasting protection to interior and exterior timber. A non-film forming, clear oil DEKS OLJE® D.1 enhances the natural beauty of the wood while being easy to maintain, requiring no sanding or stripping.

BASIC USES:

- Hardwoods and Tropical woods - Oak, Chestnut, Ash, Teak, Ipe, Mahogany, Bangkirai...
- Softwoods - Pine, Larch, Spruce...
- Exterior - Decks, Garden Furniture, Windows, Doors, Frames...
- Interior - Flooring, Panelling, Stairs, Joinery...
- Marine - Hulls, Portals, Trim, Wheel House...
- Horizontal and vertical surfaces.
- Excellent primer for conventional single pack marine and decorative coatings.

PROPERTIES:

- Optimised for thick, dense, oily and difficult to impregnate woods.
- Drives out moisture and air by penetrating deep into the wood pores - Protects against the effects of moisture.
- Transparent - Maintains the woods natural appearance.
- Natural matt sheen finish (For a gloss finish topcoat with DEKS OLJE® D.2*).
- Non film forming - No peeling, No flaking.
- Easy maintenance - No stripping or sanding.
- Can be applied above and below the water line (must be overcoated with a suitable finish below the water line).

FINISH

Matt

SIZES

1L, 2.5L, 10L, 20L, 200L

USAGE

Interior/Exterior



CLEAR

TECHNICAL DATA

Vehicle Type	Alkyd-Urethane Resins
Solvent Type	Solvent
Specific Gravity (at 20°C):	0.850 ±0.05
Viscosity	30-36 cP@25°C
Solid Content	27% ±2
Flash point	> 60°C
Shelf Life	2 years in original unopened packaging
VOC	EU limit value for this product (cat. A/I) 700 g/L (2010). This product contains max. 625 g/L.
Application Tools	Brush, Roller
Dilution	Use as is. Do not dilute.
Coverage	Initial: 1 to 4 m ² per litre. Maintenance: 8 to 12 m ² per litre. Actual coverage will vary depending on application method, type, texture and porosity of the wood.
Drying Times	24 hours, depending on temperature and humidity.
Setting up time before use or finishing with DEKS OLJE® D.2*	3 days
Clean-up	Clean all tools and equipment with white spirits while still wet. If allowed to dry, remove with paint stripper. Wipe up any drips or runs immediately with a cloth soaked in white spirits. Dried DEKS OLJE® D.1 may be removed with DILUNETT®*. Note: DEKS OLJE D1 is not classed as flammable, however, any rags, steel wool etc. soaked in DEKS OLJE D1 may spontaneously combust if improperly discarded. Rags etc. must be saturated in water; placed in a sealed, water filled metal container or laid flat and air dried before disposing with house hold waste.
Storage	Left over DEKS OLJE® D.1 should be transferred to a smaller, airtight, closed metal or glass container. Keep from freezing and high temperature.

GOOD APPLICATION PRACTICE

Cover everything you do not wish to paint.
Apply between 5°C and 35°C.
Do not apply in direct sunlight or to hot surfaces.

SURFACE PREPARATION

General Directions:

Surfaces must be clean, dry and free of dirt, grease, grime, mildew and previous coatings.

Treat mildew with a 50/50 bleach/water solution. Scrub solution on to surface and allow to stand for 10-15 minutes; rinse thoroughly.

After stripping and cleaning, allow wood to dry 2-3 good drying days or until it has reached a moisture content of 18 % or less before applying finish.

DEKS OLJE® D.1 may only be applied to bare wood surfaces or a wood surface that was previously finished with DEKS OLJE® D.1. ALL other finishes must be completely and thoroughly removed.

If necessary, sand surface after cleaning and/or stripping.

New wood:

Interior - Sand wood with 100 grit paper or coarser depending on wood species to open the pores, dust off and wipe with a cloth soaked in Methylated Spirits to degrease the surface and remove any remaining sanding residue.

Exterior - New smooth, planed wood has a hard shiny surface called mill-glaze that prevents maximum penetration and adhesion of any finish, this should be removed to ensure maximum performance of the finish.

Treat with AQUANETT®* or PREPDECK®* and neutralise with NET-TROL®* OR sand with 80 grit or coarser depending on wood species to open the wood pores. Dust off and wipe with a cloth soaked in Methylated Spirits to degrease the surface and remove any remaining sanding residue.

Iroko, Padouk: see "restrictions".

Weathered wood surfaces (untreated):

Wood that has weathered longer than 12 months should be cleaned with NET-TROL®* to remove all loose wood fibres, dirt and other surface contamination. If wood is severely contaminated, clean with AQUANETT®* or PREPDECK®* and neutralise with NET-TROL®*.

Previously coated surfaces (oiled, paint, stain, varnish...):

All previous coatings must be completely and thoroughly removed.

Oils and sealers: Strip with AQUANETT®* or PREPDECK®*, neutralise with NET-TROL®*.

Solvent (oil or alkyd-based finishes): Strip with DILUNETT®* neutralise with NET-TROL®*.

Acrylic (Water-based) finishes: Strip with PREPDECK®* neutralise with NET-TROL®*.

Other finishes e.g. 2 pack epoxies, urethanes... Strip with DSP 800*, neutralise by mechanically sanding or rinse surface with a suitable solvent - Warrar Water, Acetone, White Spirits...

Note: Hardwoods and woods rich in tannins e.g. Oak, Chestnut, Teak, Ipe, Cedar... may darken with AQUANETT®*, PREPDECK®* and DILUNETT®*, neutralising with NET-TROL®* immediately after rinsing will lighten and restore the woods colour

APPLICATION

The secret of DEKS OLJE® D.1's success lies in its saturation of the wood to bring about an even "ratt sheen" finish when dry.

Start by applying DEKS OLJE® D.1 to an area that can be treated in about 15 minutes.

As soon as the 1st application has penetrated (normally 15-30 minutes), apply a 2nd application.

Continue applying DEKS OLJE® D.1 "wet on wet" until a uniform, overall saturation of the wood is achieved. The number of applications needed depends on the wood.

DO NOT allow DEKS OLJE® D.1 to become dry or touch dry between applications.

Leave final application 30 minutes, then wipe over the surface to remove excess and puddled material with a rag soaked in

DEKS OLJE® D.1 and rung out so that it is damp to the touch. If necessary, occasionally ring out the cloth to keep it damp.

It is important that as much DEKS OLJE® D.1 as possible is applied on the first day.

DEKS OLJE® D.1 must be kept "active", this is done by the "wet on wet" applications and the continual brushing over of the area, which assists and helps achieve maximum penetration.

DEKS OLJE® D.1 has high penetration; its place is in the wood and not as a surface coating.

Allow 3 days for DEKS OLJE® D.1 to set-up and dry, before putting the boat in service or continuing with DEKS OLJE® D.2*.

Temperature is of very little importance when applying DEKS OLJE® D.1.

MAINTENANCE

Regular washing with NET-TROL®* will help to maintain the appearance of DEKS OLJE® D.1.

DEKS OLJE® D.1 will gradually lighten over time due to exposure to the sun and UV rays.

When the wood has lightened to a light grey colour, it is time for a maintenance application.

Clean surface with NET-TROL®*.

Apply DEKS OLJE® D.1 until wood is saturated and the finish restored, usually 1 or 2 applications will be sufficient.

RESTRICTIONS

DEKS OLJE® D.1 may soften some caulking. If in doubt consult us.

The tannins and natural oils in woods such as Iroko impede the penetration and drying of finishes. These species of wood should be thoroughly prepared or allowed to weather for 12 months before applying DEKS OLJE® D.1. Contact us for preparation advice.

Plywood - Contact us.

Do not use DEKS OLJE® D.1 on Therra treated wood.

SAFETY

Refer to the safety data sheet (SDS) available at www.owatrol.com and the text on the label. Keep out of the reach of children.

*Same Manufacturer. *Refer to the TDS.

This Technical Data sheet cancels and replaces any previous Technical Data sheet for the same product. Its purpose is to inform the user about the product. The information contained within this Technical Data sheet is based on our current knowledge. However, the information contained within this document cannot replace a specification appropriate to the nature and conditions of the substrate to be coated. Due to ongoing technical advances, it is the responsibility of the user to establish that this document has not been superseded by a more recent edition. The information contained within this document is for guidance only and the manufacturer is unable to guarantee or accept responsibility for the results as it has no control over the conditions under which its products are applied.

Publication Date: 20/02/2024

DURIEU S.A.

91070 Bondoufle - France
Tél +33 (0)1 60 86 48 70

OWATROL INTERNATIONAL S.L.U

08006 Barcelona - Spain
Tél. +34 93 125 88 68

Owatrol® is a trademark



Discover all our solutions at
www.owatrol.com

Our technical department is at your disposal
to answer any questions, you may have at
info@owatrol.com